

Technical Data Sheet

Foam | Neoprene / EPDM / SBR Blend | 1260

Our 1260 neoprene blend is a RE43/2A3 grade, black closed-cell foam used in various applications. The density is 7 – 11 PCF / 112 – 176 kg/m³ with a service temperature range of - 40 °F to 200 °F (high continuous use) or 250°F (high intermittent use). It has a Resilience rating of 20%.

Item	Specs		Test Method
Grade	RE43/2A3		
Density (PCF) (kg/m ³)	7 – 11 PCF 112 - 176 kg/m ³		ASTM D 1056
Compression Deflection (CFD) (psi) (kPa) @25%	9 – 13 psi 62 – 89 kPa		ASTM D1056
Shore Hardness OO (Durometer)	55 – 65		ASTM D 2240
Compression Set %	≤ 30		ASTM D1056
Tensile Strength (psi)(kPa)	100 psi 689 kPa		ASTM D412
Elongation (%)	125		ASTM D412
Tear Strength Resistance (ppi) (lb/in)	15		ASTM D 624
Water Absorption by Weight %	< 10		ASTM D 1056
Accelerated Age Testing: 7 Days @ 158 °F Chang in CD	± 30% max		ASTM D1056
Service Temperature (°F)(°C)	°F	°C	
Low	-40	-40	
High Continuous	200	93	
High intermittent	250	121	
Flame Resistance	Pass 2.5mm and higher HF-1: 1.4 - 1.8mm HBF: 1.8mm and higher		FMVSS 302 UL94 listed
Industry and OEM Specifications: Jacobs and Thompson Inc. certifies that the following product meets the required specifications;	MS-Z-75 J18 2A3 SAE J18 APR2002 2A3 ASTM D1056-14 2A3 GMN11106 TYPE II GMW15473 CLASS I TYPE V GMW17408 Class I Type V WSK-M2D-419A TYPE 4 TSM1501G 2A3		

REV. 009
REV. DATE: 09/30/18
ISO 9001:2015 • ISO/IEC 17025:2017

Jacobs & Thompson cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. Unless otherwise agreed in writing, we sell the products without warranty and users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purpose.

Head Office: 89 Kenhar Drive,
Ontario M9L 2R3
Tel: (416) 749-0600
info@foamparts.com
FoamParts.com