

Technical Data Sheet

Foam | PVC | 1336

Our 1336 is a closed-cell 6 PCF / 96 kg/m³ PVC foam. This material is used for a wide variety of automotive gasketing applications. It has a (90°) Peel Adhesion of 20 oz/in.

Item	Specs		Test Method
Grade			
Density (PCF) (kg/m ³)	6 PCF 96 kg/m ³		ASTM D 1667
Compression Deflection (CFD) (psi) (kPa) @30%	0.5 psi 3.4 kPa		ASTM D 1667
Shore Hardness OO (Durometer)			
Compression Set (%)	4		NTP 37
Tensile Strength (psi)(kPa)	13.7 psi 94 kPa		ASTM D 412 Die A
Elongation (%)	125		ASTM D 412 Die A
Tear Strength Resistance (ppi)			
Water Absorption by Weight (%)	5		NTP 35
Accelerated Age Testing:			
Service Temperature (°F)(°C)	°F	°C	
Low			
High Continuous			
High intermittent			
Flame Resistance			
Industry and OEM Specifications: Jacobs and Thompson Inc. certifies that the following product meets the required specifications;	GM 6086 TYPE 1A MS-AY500 Type 2		

REV. 002

REV. DATE: 09/30/18

ISO 9001:2015 • ISO/IEC 17025:2017

Jacobs & Thompson cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. Unless otherwise agreed in writing, we sell the products without warranty and users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purpose.

Head Office: 89 Kenhar Drive,
Ontario M9L 2R3
Tel: (416) 749-0600
info@foamparts.com
FoamParts.com