

### Technical Data Sheet

#### Textiles & Films | Felts | 1990

Jacobs and Thompson Inc. certifies that the following product meets the required specifications: **ESB- M6G17-A; MS-JZ8-22; GM 6420M.**

Property	Specification	Test Method
Construction	100% Nylon	
Weight	7.6 OPSY (258 g/m <sup>2</sup> )	
Abrasion Resistance Wet: (CS-10wheel/500g load) Dry: (CS-10wheel/1000g load) Heat Aged: (7 days @ 82°C) (CS-10wheel/500g load)	1000 + cycles 1500 + cycles 1500 + cycles	
Scuffing Resistance (900g load / scuffing head A)	2000 + cycles	FLTM BN 8-4-4
Fogging	90 + units	SAE J1756/FLTM40116-3
Xenon	Pass	SAE J1885 (225KJ-144 hrs)
Flammability	Pass	GM9070P/FMVSS 302

REV. 005  
REV. DATE: 09/30/18  
ISO 9001:2015 • ISO/IEC 17025:2018

Jacobs & Thompson cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. Unless otherwise agreed in writing, we sell the products without warranty and users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purpose.

Head Office: 89 Kenhar Drive,  
Ontario M9L 2R3  
Tel: (416) 749-0600  
info@foamparts.com  
FoamParts.com