

Technical Data Sheet

Textiles & Films | Polyester Fabrics | FB217, FB218, FB439, FB502

Property	Specification	Test Method
Item No.	FB502, FB217, FB218, FB439 Brushed Polyester	
Description	100% brushed polyester tricot	
Denier Size	50D/50D	
Thread Count	24F, 28G	
Weight	135 ± 5 gm/l.yd	
Coating	N/A	
Finish	Heat set at 170°C	
Width	62/63"	
Surface Abrasion (H-18 wheels, 1000g load)	Average No. cycles passed 300 cycles	ASTM D3884-92 (Taber)
Breaking Strength (1BF)	7 kgs/cm ²	ASTM D5034-95 (Grab)
Tearing Strength (1BF)	Warp 14.879 kgs Fill 9.794 kgs	ASTM D2262-83 (Tongue)

REV. 002
REV. DATE: 09/30/18
ISO 9001:2015 • ISO/IEC 17025:2017

Jacobs & Thompson cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. Unless otherwise agreed in writing, we sell the products without warranty and users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purpose.

Head Office: 89 Kenhar Drive,
Ontario M9L 2R3
Tel: (416) 749-0600
info@foamparts.com
FoamParts.com