

Technical Data Sheet

Textiles & Films | Polyester Fabrics | FB268, FB312, FB381, FB390, FB422,  
FB466, FB480, FB671, FB696, FB697

| Property      | Specification        | Test Method |
|---------------|----------------------|-------------|
| Fiber content | 100% polyester       |             |
| Style         | 2700                 |             |
| Description   | Interlock            |             |
| Weight        | 112 g/m <sup>2</sup> |             |
| Width         | 58/60"               |             |
| Heat set      | 350 °F               |             |
| Shrinkage     | 4x4                  |             |
| Construction  | Circular             |             |

REV. 002  
REV. DATE: 09/30/18  
ISO 9001:2015 • ISO/IEC 17025:2017

Jacobs & Thompson cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. Unless otherwise agreed in writing, we sell the products without warranty and users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purpose.

Head Office: 89 Kenhar Drive,  
Ontario M9L 2R3  
Tel: (416) 749-0600  
info@foamparts.com  
FoamParts.com